





TRUTH IN TESTING



HEAD TO HEAD COMPARISON TEST

RHINO HYDE (80A BLUE)
 VS.
 BLUE OX (85A)



STANDARD TEST TYPE	ASTM #	BLUE OX™	STANDARD RHINO HYDE™
DUROMETER	D2240	85A	80A
TENSILE	D412	3430 PSI	5500 PSI
ELONGATION	D412	675%	800%
TEAR STRENGTH (DIE C)	D624	330 PLI	575 PLI
SPLIT TEAR	D624	210 PLI	400 PLI
TABER (LOWER # = LESS WEAR)	D4060	22.4 MG	15.3 MG

RHINO HYDE

TRUTH IS IN THE TESTING!!!